

Product: 2000



Dry Adhesion (lbf)	
Aluminum	20.7/70c
Brick	24.9/90c
Concrete	29.7/100c
Galvanized Steel	24.2/90c
Glass	24.2/98c
Kynar	20.3/100c
Luan (Wood)	23.5/100c
Steel	24.8/100c
Tile	26.5/100c
Vinyl	20.0/95c
Tensile at Peak (psi)	259
Elongation at Break (%)	236
Type "A" Hardness	41
Tack Free time (ASTM method)	15 min
Cure rate (1/4 x 1/4 bead)	3 days

Geocel, LLC
P.O. Box 398
Elkhart, IN 46515

Questions?
Call Customer Service at 800-348-7615

12/10