

Product: ProFlex RV IRR



Dry Adhesion (lbf)	
Aluminum	21.90/80c
Brick	22.64/100a
Concrete	18.67/100c
Galvanized Steel	24.15/100a
Luan (Wood)	23.23/100a
Steel	19.83/80c
Vinyl	15.32/100a
Tensile at Peak (psi)	252.4
Elongation at Break (%)	488.61
Type "A" Hardness	45
Tack Free time (ASTM method)	4 hours
Cure rate by weight loss (internal)	5 days

Geocel, LLC
P.O. Box 398
Elkhart, IN 46515

Questions?
Call Customer Service at 800-348-7615

04/09