

Product: 2300 MHRV



Dry Adhesion (lbf)	CLEAR	WHITE	BRIGHT WHITE
Aluminum	21.82/100c	23.76/100c	21.78/100c
Brick	21.55/100c	24.08/100c	23.45/100c
Concrete	24.89/100c	23.14/100c	23.17/100c
Galvanized Steel	16.43/100c	20.90/100c	20.43/100c
Glass	24.12/100c	21.66/100c	22.20/100c
Kynar	21.54/100c	21.25/100c	20.15/100c
Luan (Wood)	23.99/100c	23.68/100c	24.07/100c
Steel	21.42/100c	12.46/100c	18.40/100c
Tile	26.92/100c	22.23/100c	21.34/100c
Vinyl	18.45/100c	20.54/100c	18.63/100c
Tensile at Peak (psi)	94.6	61.31	107.83
Elongation at Break (%)	421.8	308.93	483.76
Type "A" Hardness	46	42	48
Tack Free time (internal method)	20 mins	60 mins	20 mins
Tack Free time (ASTM method)	3 hours	150 mins	60 mins
Cure rate (1/4 x 1/4 bead)	5 days	48 hours	2 days

Geocel, LLC
P.O. Box 398
Elkhart, IN 46515

Questions?
Call Customer Service at 800-348-7615

11/09