

**Product: 2300**



<b>Dry Adhesion (lbf)</b>	<b>Clear</b>	<b>Colors</b>
Aluminum	16.44/100a	13.07/100a
Concrete	21.04/100a	17.74/100a
Galvanized Steel	23.33/50c	14.47/100a
Glass	20.07/10c	20.30/100a
Kynar	22.93/60c	24.23/100a
Luan (Wood)	17.09/100a	20.46/100a
Shingle	5.23/sf	6.68/100a
Tile	30.02/55c	23.96/100a
Vinyl	18.57/90c	11.90/100a
Tensile at Peak (psi)	224.42	518.69
Elongation at Break (%)	1025.55	994.16
Type "A" Hardness	39	36
Tack Free time (ASTM method)	2 hours	2 1/2 hours
Cure rate (1/4 x 1/4 bead)	1 day	1 day

Geocel, LLC  
P.O. Box 398  
Elkhart, IN 46515

Questions?  
Call Customer Service at 800-348-7615

09/09