

**Product: 8125**



<b>Dry Adhesion (lbf)</b>	<b>CLEAR</b>	<b>WHITE</b>
Aluminum	13.29/100c	11.66/100c
Brick	14.56/100c	7.00/100a
Concrete	12.57/100c	12.42/100c
Glass	12.16/100c	12.22/100c
Steel	12.75/100c	11.52/100c
Tile	13.51/100c	12.90/100c
Tensile at Peak (psi)	243.93	144.73
Elongation at Break (%)	557.5	465
Type "A" Hardness	34	34
Tack Free time (ASTM method)	15 mins	15 mins
Cure rate (1/4 x 1/4 bead)	2 days	2 days

Geocel, LLC  
P.O. Box 398  
Elkhart, IN 46515

Questions?  
Call Customer Service at 800-348-7615

03/09

07/09