

Product: 4500



<b>Dry Adhesion (lbf)</b>	<b>WHITE</b>	<b>BLACK</b>
Aluminum	11.71/100c	13.72/100c
Brick	10.34/90c	14.12/100c
Concrete	12.56/100c	14.73/100c
EPDM (White or Black)	5.16/20c	9.01/100c
Galvanized Steel	10.56/100c	15.00/100c
Glass	11.31/100c	14.77/100c
Luan (Wood)	11.80/100c	13.07/100c
Steel	11.54/100c	13.40/100c
Tile	11.30/100c	15.38/100c
Vinyl	11.11/100c	13.12/100a
Tensile at Peak (psi)	106.99	251.7
Elongation at Break (%)	428.33	375.8
Type "A" Hardness	29	40
Tack Free time (ASTM method)	40 mins	105 mins
Cure rate (1/4 x 1/4 bead)	2 days	1 day

Geocel, LLC  
P.O. Box 398  
Elkhart, IN 46515

Questions?  
Call Customer Service at 800-348-7615

07/09

02/09