

Product: PUR 52



Dry Adhesion (lbf)	
Aluminum	20.0 / 100 C
Brick	27.1 / 60 C
Concrete	27.2 / 100 C
Fiberglass	24.2 / 100 C
Kynar	20.4 / 100 C
Luan (Wood)	16.6 / 80 C
Steel	22.2 / 100 C
Tile	22.4 / 75 C
Tensile at Peak (psi)	264
Elongation at Break (%)	1252
Type "A" Hardness	42.63
Tack Free time (ASTM method)	110 min.
Cure rate (1/4 x 1/4 bead)	72 h

Geocel, LLC
P.O. Box 398
Elkhart, IN 46515

Questions?
Call Customer Service at 800-348-7615

02/09